

Polyethylene

Visico™ LE4423 / Ambicat™ LE4437

Silane Crosslinkable Insulation Compound

Description

Visico™ LE4423/ Ambicat™ LE4437 is a silane crosslinkable natural compound system designed for insulation of low voltage energy cables.

Visico LE4423 is a low density polyethylene, copolymerized with vinyl silane. Ambicat LE4437 is a crosslinking catalyst masterbatch specially designed to be used with Visico base resins. The system crosslinks quickly in sauna or in hot water.

Cable insulation with a proper mixture of Visico LE4423 (95 parts) and Ambicat LE4437 (5 parts) exhibits excellent thermo-oxidative stability. The combination is suitable for both copper and aluminum conductors. Ambicat LE4437 contains a copper passivator, which minimizes discoloration (blackening) of the conductor.

Typical characteristics

Visico™ LE4423 / Ambicat™ LE4437 can be described with following typical characteristics:

| | |
|---|--|
| Excellent processing properties | Less smell; more consistent quality (no volatiles) |
| Low scorch allowing long runs and more frequent tooling changes | Good curing speed |
| Excellent surface finish | No drying prior to extrusion |
| Minimal discoloration of conductor | Excellent storage stability |

Applications

Visico™ LE4423 / Ambicat™ LE4437 is intended for following applications:

Insulation of low voltage energy cables, range up to 6 kV

Specifications

Visico™ LE4423 / Ambicat™ LE4437 is expected to meet the applicable requirements included in the below mentioned standards provided it is processed using sound material handling and processing practices as well as appropriate testing procedures.

| | |
|--|--------------|
| Canadian Standards Association C22.2 No. 38 Cable Types RW-90 and RWU-90 | IEC 60502-1 |
| EN 50290-2-29 | NBN C 33-321 |
| HD 603 S1 | NF C33-210 |

The standards refer to above are a selection and is not complete coverage of all applicable standards. Contact your Borealis representative for additional information.

Visico™/Ambicat™ are trademarks of the Borealis Group



Polyethylene

Visico™ LE4423 / Ambicat™ LE4437

Physical properties

| Property | Typical value * | Unit | Test method |
|---|-----------------|-------------------|---------------|
| Density ¹ | 923 | kg/m ³ | ISO 1183-1 |
| Density ² | 935 | kg/m ³ | ASTM D792 |
| Melt flow rate (190 °C/2.16 kg) ¹ | 1.0 | g/10min | ISO 1133-1 |
| Hot Creep Test (150°C, 29 psi) Permanent deformation ³ | 0 | % | ICEA T-28-562 |
| Hot Creep Test (150°C, 29 psi) Elongation under load ³ | 60 | % | ICEA T28-562 |
| Tensile strength (250 mm) ³ | >2200 | psi | ASTM D638 |
| Elongation at Break ³ | >300 | % | ASTM D638 |
| Change of tensile properties After ageing 121 °C, 168h ⁴ | ≤20 | % | ASTM D638 |

* Data should not be used for specification work

¹ Base resin

² Masterbatch

³ Addition of 5% Catalyst masterbatch

⁴ Addition of 5% Catalyst masterbatch.

These values are based on sufficient crosslinked/cured Visico. If Visico is not sufficiently crosslinked the material will continue to crosslink during the ageing procedure and a larger change between values before and after ageing may occur

Electrical properties

| Property | Typical value * | Unit | Test method |
|----------------------------------|-----------------|------|-------------|
| Dielectric constant ⁵ | 2.3 | - | ASTM D150 |

* Data should not be used for specification work

⁵ 60 Hz, Addition of 5% Catalyst masterbatch

Processing techniques

Extrusion:

Visico LE4423/Visico LE4437 are suitable for most equipment designed for PVC/PE extrusion

| Processing setting | Typical value/range |
|----------------------|---------------------|
| Barrel temperature 1 | 295 °F |
| Barrel temperature 1 | 145 °C |
| Barrel temperature 2 | 330 °F |
| Barrel temperature 2 | 165 °C |
| Barrel temperature 3 | 340 °F |
| Barrel temperature 3 | 170 °C |
| Barrel temperature 4 | 340 °F |
| Barrel temperature 4 | 170 °C |
| Die head temperature | 350 °F |
| Die head temperature | 175 °C |

Visico™/Ambicat™ are trademarks of the Borealis Group



Polyethylene

Visico™ LE4423 / Ambicat™ LE4437

The temperature of the melted polymer during extrusion should preferably not exceed 200°C. Having the above set temperature profile, a stable extrusion process and a cable having smooth glossy appearance should be achieved. On-size pressure or draw down tube-on tooling is preferred. The use of a gradient cooling bath will improve the cable insulation physical properties further.

Conductor preheating up to 100°C is recommended when producing cables with a conductor up to 16 mm² for good mechanical properties.

Crosslinking:

These products can be crosslinked in room temperature, by immersion in hot water or exposed to low pressure steam at a temperature up to 90°C. This time period may be varied due to the humidity, thickness of insulation, reel size and temperature.

Packaging and storage

LE4423 - Base material is protected from moisture ingress

Package: Octabins
Smallbins

LE4437 - Catalyst master batch is protected from moisture ingress

Package: Bags
Smallbins

Visico LE4423/Visico LE4437 has excellent storage stability. Visico LE4423 and Visico LE4437 can be stored for 18 months after production, at 10-30°C (50-85°F) in unopened original packages, without significant deterioration in the quality of the material. Visico LE4423 and Visico LE4437 should be stored in dry conditions and protected from direct sunlight. Improper storage can initiate degradation, which results in odor generation and color changes and can have negative effects on the physical properties of this product. Visico LE4437 is sensitive to moisture and is therefore delivered with low moisture content, ready to be used. Pre-drying is not recommended, as it will destroy the drying agent that has been added to prevent the material to take up moisture. The bags must be properly resealed between uses, as even short periods of storage in humid conditions may cause scorch during extrusion.

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.