

Polyethylene

BorPure™ MB7541

High Density Polyethylene for Injection and Compression Moulding

Description

BorPure MB7541 is a multimodal High Density Polyethylene intended for injection and compression moulding with a strong focus on easy process ability, excellent organoleptic performance and high environmental stress cracking resistance (ESCR) in combination with good impact strength allowing further down weighting and consequently waste reduction. The improved processability of this grade, even at low melt temperature, allows energy savings and faster cycle time.

Cas No. 25087-34-7

Typical characteristics

BorPure MB7541 can be described with following typical characteristics:

Excellent easy process ability	Good environmental stress crack resistance (ESCR)
Very good organoleptic properties	Good impact strength

Applications

BorPure™ MB7541 is intended for following applications:

Caps and closures for beverage and food	Consumer and industrial articles for demanding environment
Caps and closures for industrial packaging	Transport packaging

Physical properties

Property	Typical value *	Unit	Test method
Density	954.0	kg/m³	ISO 1183-1
Melt flow rate (190 °C/2.16 kg)	4.00	g/10min	ISO 1133-1
Hardness, Shore D	61	-	ISO 868
Tensile Impact strength, notched (23°C)	80	kJ/m²	ISO 8256/1A
Tensile Impact strength, notched (23°C)	80	kJ/m²	ISO 8256/1A
Heat deflection temperature B (0.45 MPa)	65	°C	ISO 75-2
Tensile modulus (1 mm/min)	850	MPa	ISO 527-2
Tensile stress at yield (50 mm/min)	22	MPa	ISO 527-2
Tensile strain at yield (50 mm/min)	10	%	ISO 527-2
Environmental stress crack resistance (Igepal 10γ F50)	40	h	ASTM D 1693-B

* Data should not be used for specification work

Processing techniques

BorPure MB7541 is easy to process with standard injection moulding machines. Following moulding parameters should be used as guidelines:

BorPure™ is a trademark of the Borealis Group



Polyethylene

BorPure™ MB7541

Processing setting	Typical value/range
Melt temperature	190 - 250 °C
Mould temperature	10 - 40 °C
Injection speed	As high as possible °C

Shrinkage 1 - 2 %, depending on wall thickness and moulding parameters

Packaging and storage

BorPure MB7541 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which can result in odour generation and colour changes and can have negative effects on the physical properties of this product.

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency. Further information on sustainability and Design for Recycling (DfR) can be found from our websites www.borealisgroup.com and www.borealiseverminds.com.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.