

Polypropylene

BorPure™ RJ378MO

Polypropylene Random Copolymer for Injection Moulding

Description

BorPure RJ378MO is a specially modified high MFR transparent polypropylene random copolymer based on proprietary Borealis Nucleation Technology (BNT), combining outstanding organoleptic performances (low taste, low odour) together with high flowability making it ideal solution for thin walled packaging and houseware dedicated for food contact applications. BorPure RJ378MO offers fast crystallization speed together with high transparency with a tinge of blue delivering benefits towards all parts of the value chain. This grade, designed for high-speed injection moulding, contains nucleating and demoulding additives.

Cas No. 9010-79-1

Typical characteristics

BorPure™ RJ378MO can be described with following typical characteristics:

Easy processing	Excellent organoleptic properties
Fast crystallisation speed	Good stiffness and impact balance
Outstanding aesthetics & transparency with tinge of blue	

Applications

BorPure™ RJ378MO is intended for following applications:

Caps and closures	Pails
Houseware	Thin wall containers
Lids	
Transparent food containers	
Squared containers	

Physical properties

Property	Typical value *	Unit	Test method
Density	905	kg/m ³	ISO 1183-1
MFR 230°C/2.16kg	45.0	g/10min	ISO 1133-1
Flexural modulus	1100	MPa	ISO 178
Tensile modulus (1 mm/min)	1100	MPa	ISO 527-2
Tensile strain at yield (50 mm/min)	12	%	ISO 527-2
Tensile stress at yield (50 mm/min)	28	MPa	ISO 527-2
Charpy impact strength, notched (23 °C)	4.0	kJ/m ²	ISO 179-1/1eA
Heat deflection temperature B (0.45 MPa)	75	°C	ISO 75-2

* Data should not be used for specification work

Processing techniques

BorPure RJ378MO is easy to process with standard injection moulding machines

BorPure™ is a trademark of the Borealis Group



Polypropylene

BorPure™ RJ378MO

Processing setting	Typical value/range
Melt temperature	220 - 260 °C
Holding pressure ¹	200 - 500 bar
Mould temperature	15 - 40 °C
Injection speed	High

¹ Minimum to avoid sink marks

Shrinkage 1 - 2 %, depending on wall thickness and moulding parameters

Packaging and storage

BorPure™ RJ378MO should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which can result in odour generation and colour changes and can have negative effects on the physical properties of this product.

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available on our website www.borealisgroup.com.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.