

Polypropylene

RJ908MO

Polypropylene Random Copolymer

Description

RJ908MO is a transparent polypropylene random ethylene copolymer with high melt flow. This clarified product is designed for high speed injection moulding at low temperature and contains antistatic additives.

This polymer is a CR (controlled rheology) grade with narrow molecular weight distribution giving low warpage. Products originating from this grade have excellent transparency and gloss, and good balance of stiffness and impact strength at ambient temperatures.

Cas No. 9010-79-1

Typical characteristics

RJ908MO can be described with following typical characteristics:

Excellent flow behaviour	Good clarity
Excellent processability	Good gloss
Very good optical properties	Good stiffness and impact balance

Applications

RJ908MO is intended for following applications:

Products with complicated geometry	Lids
Transparent storage crates and boxes	Houseware containers

Articles with rather long and narrow flow lengths

Physical properties

Property	Typical value *	Unit	Test method
Density	905	kg/m ³	ISO 1183-1
Melt flow rate (230 °C/2.16 kg)	80.0	g/10min	ISO 1133-1
Flexural modulus	1100	MPa	ISO 178
Tensile modulus (1 mm/min)	1150	MPa	ISO 527-2
Charpy impact strength, notched (23 °C)	4.2	kJ/m ²	ISO 179-1/1eA
Heat deflection temperature B (0.45 MPa)	80	°C	ISO 75-2

* Data should not be used for specification work

Processing techniques

RJ908MO is easy to process with standard injection moulding machines.

Packaging and storage

RJ908MO should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which can result in odour generation and colour changes and can have negative effects on the physical properties of this product.

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

Polypropylene

RJ908MO

Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency.

Further information on sustainability and Design for Recycling (DfR) can be found from our websites www.borealisgroup.com and www.borealiseverminds.com.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.